

# TOWN & COUNTRY

SURFACES

SKID TEST WITH ANSI A326.3:2017 : "Test method for measuring Dynamic Coefficient Of Friction of hard surface flooring materials"

Collection Product Reference:

**T-739 Burano**

SIZE :	FINISH :	THICKNESS :	D A T E:
24" X 24"	Matte	10MM	11/20/2023

SUBJECT MATERIAL TESTED: T-739 BURANO IVORY

- The specimens were cleaned before testing
- Three (3) specimens were tested in all four directions with 4"long measurements.
- The SBR sensor was verified using a standard tile prior to testing.
- Testing was performed under wet conditions using 0.05% SLS water
- Testing was conducted under laboratory conditions at approximately 70°F and 50% relative humidity .
- using a calibrated BOT 3000E RSI device
- After testing, the SBR sensor was verified again according to the procedure.

#### TEST RESULTS

Direction	Sample 1	Sample 2	Sample 3
1	0,54	0,54	0,51
2	0,54	0,55	0,52
3	0,51	0,53	0,54
4	0,54	0,53	0,53
Average	0,53	0,54	0,53

AVG DCOF COEFFICIENT	0,53
----------------------	------

COMMENTS :

#### Specifications:

According to the ANSI A326.3, "Unless otherwise specified, hard surface flooring materials suitable for level interior spaces expected to be walked upon when wet with water shall have a wet DCOF of 0.42 or greater when tested using SBR sensor material and SLS solution as per this standard.

Protocol n° 160

Laboratory Technician

