

Bora Tomar - Technical specifications

ISO13006 - EN14411 - ISO10545 Standards

Nominal sizes (cm): 4,8x20	Thickness (mm) : 9.5
Sides: natural	Surface: natural
	Product Group: Town & Country Surfaces

Technical characteristics		Test method	EN 14411 and ISO 13006 requirements	Italcer Average values
Dimensions	Length and width	ISO 10545-2	±0.6% and ± 2.0mm	Compliant
	Straightness of sides	ISO 10545-2	±0.5% and ± 1.5mm	Compliant
	Rectangularity	ISO 10545-2	±0.5% and ± 2.0mm	Compliant
	Flatness	ISO 10545-2	±0.5% and ± 2.0mm	Compliant
	Thickness	ISO 10545-2	±5% and ± 0.5mm	Compliant
Water absorption		ISO 10545-3	≤ 0.5%	Compliant
Modulus of rupture		ISO 10545-4	≥ 35 N/mm ²	Compliant
Breaking strength (S)		ISO 10545-4	≥ 1300 N	Compliant
Abrasion resistance		ISO 10545-7	Declared class	PEI 3(Peach Puree); PEI 4 (Laguna Azul,Blue Hawaian, Cuba Libre,Mint Julep, Tequila Daisy); PEI 5(Chelsea Sidecar, Genonic)
Linear thermal expansion		ISO 10545-8	Declared value	$\alpha \leq 7.1 \times 10^{-6} \text{ }^{\circ}\text{C}^{-1}$
Thermal shock resistance		ISO 10545-9	No alterations	Resistant
Frost resistance		ISO 10545-12	No alterations	Resistant
Chemical resistance		ISO 10545-13	Declared value	LA – HA
Household chemicals resistance		ISO 10545-13	B min.	Compliant
Stain resistance		ISO 10545-14	Class 3 min.	Compliant
Mohs Hardness		UNI EN 101	5 Min.	Compliant
Shade variation		ANSI A 137.1	Not required	V1 (White Lady) ; V4
Fire reaction		UNI EN 13501-1	-	A1FL class
Thermal Conductivity		EN 12524	Not required	$\lambda = 1.3 \text{ W/m}^{\circ}\text{K}$
Light and colour fastness		DIN 51094	Not required	No variations z

MORE INFO:



Town & Country Surfaces

230 Fifth Avenue
Suite 1714
New York NY 10001

General Inquiries:

info@tncsurfaces.com
Phone: 212-679-0312